

## Technical Data Sheet

Page 1 of 3

- Properties:** AKEMI® Natura Impregnator is a ready for use, solvent-free impregnation based on a silane/siloxane mixture emulsified in water. The product penetrates into the pore system of the stone. A poly-siloxane results from the catalytic reaction. In addition, a reaction with the silicate substance of the stone takes place which results in high efficiency. The product is distinguished by the following qualities:
- solvent-free, no VOC
  - environmentally-friendly
  - application also possible on surfaces with residual humidity
  - neutral pH value
  - reduction of water and dirt absorption during periods of moisture
  - fast liberation of humidity during dry periods due to high vapour permeability
  - maintenance of breathing properties because there is no surface layer
  - resistance to UV radiation
  - good alkali resistance towards mineral joint mortar
  - the colour of the stone is normally not enhanced (preliminary test)
- Application Area:** AKEMI® Natura Impregnator is suited to achieve a water and dirt repellent effect on absorbent, mineral substances s.a. natural and artificial stone (polished, ground or rough surfaces of marble, limestone, granite, gneiss, porphyry, cotto, terrazzo, unglazed ceramic tiles etc.). The product is also very well suited for bricks, sand-limestone and mineral-based plaster.
- Instructions for Use:** Disregarding the processing guidelines can lead to irreparable damage!
1. Cleaning: the surface must be clean, completely dry and free from all layers. Ensure that outdoors stone does not contain any detrimental salts (nitrates, sulphates, chlorides) because these can reduce the absorptive capacity of the impregnating material. Depending on the type of stone and the degree of soiling, the following products can be recommended, please pay attention to our care recommendations as well as our Technical Data Sheets: AKEMI® Stone Cleaner, AKEMI® Concrete Film Remover, AKEMI® Rust Remover, AKEMI® Acid Cleaner, AKEMI® Intensive Cleaner, AKEMI® Algae and Moss Remover POWER or LONGLIFE, AKEMI® Wax Stripper, AKEMI® Oil and Grease Remover Paste and AKEMI® Graffiti-Remover. Rinse well with water after cleaning.
  2. Preparation of a sample area:  
Before starting we recommend to prepare a sample area of 1 - 2 m<sup>2</sup>  
In order to examine the efficiency of the impregnation, to evaluate the appearance of the treated object (colour enhancement) and to ascertain the material consumption as exactly as possible.
  3. Impregnating procedure:
    - a) The best conditions for impregnating are a cold object, an ambient temperature of 15 - 25°C and a protection from humidity for approx. 24 hours. The stone must not be warmed up by a under floor heating or direct sunlight.
    - b) The impregnating effect is sufficient for fissures which are smaller than 0.3 mm.
    - c) In general, one to two appliances wet-in-wet are sufficient.

TDS 06.21

## Technical Data Sheet

- d) Shake before use. Apply the product with a brush or a mop. Airless spraying equipment with low pressure (max. 1 bar over pressure) is suitable for treating façades using the flooding (multiple-coat) method and a jet distance of approx. 15 cm (condition: tubes and seals must be resistant to solvents). Product run-off should be avoided.
- e) Approx. 20 minutes after application, respectively before drying of the impregnation on the surface, any excess which has not been absorbed by the stone has to be completely removed with a suitable cloth. Polished surfaces must additionally be polished again until any blooming on the surface is removed.
- f) If the desired effect is not achieved or if the impregnation has been applied unevenly, it is possible to apply the impregnation once again. The water repellent effect develops after approx. 24 hours. Sufficient efficiency is reached after 1 week, complete hardening after 3 weeks.
- g) Tools can be cleaned with AKEMI® Nitro-Dilution.

### Special Notes:

- Special protective measure in case of spray application: avoid formation of aerosols and risk to third parties. Do not breathe vapours (protective mask).
- Ensure sealing of the reverse side and lateral surfaces of the stone, so that rising moisture cannot penetrate into the stone. In this context we recommend the use of AKEMI® Anti-Stain Coating 2015 to seal the reverse side and the lateral surfaces.
- In case of loose laying outdoors it is recommended to treat the stone prior to laying from all sides with AKEMI® Natura Impregnator.
- Impregnations do not offer sufficient protection against water-logging.
- If the treated area is cleaned, a drying time of 1 - 2 days (depending on the temperature) is necessary.
- A treatment with AKEMI® Natura Impregnator prevents the stone from getting dirty again, respectively, the process will be delayed considerably. Should the surface become dirty again it can be cleaned much more easily.
- Unsuitable or aggressive cleaning agents as well as pressure washers may destroy the impregnation and the stone. We recommend using AKEMI® Mild Stone Soap or AKEMI® Crystal Clean only for the regular cleaning.
- Product which has been inaccurately applied, can possibly be removed with AKEMI® Impregnation Remover.
- Existing joints must be tested in view of their resistance to solvents. In case wetting agents had been used to smoothen joint fillers, they must be removed prior to application of the impregnation.
- AKEMI® Natura Impregnator is not suited for glazed and non-absorbent surfaces.
- In case of a water absorption of the stone of less than 3% in weight we recommend to use our solvent-containing products AKEMI® Stone Impregnation or Duro Impregnator.
- A surplus of the product causes blooming and spotting.
- Surfaces to be treated must be protected against direct solar radiation.
- Protect synthetic materials which are not resistant to solvents, window-screens, parts to be varnished or objects situated in the area of working (cars, gardens).

**Technical Data Sheet**

Page 3 of 3

- An evaluation of the impregnation according to its water repellent effect is not sufficient because this effect shows on the surface only. The water repellent effect can be diminished or be invisible due to dust settings.
- The colour of most stone surfaces will not or only slightly change. On quartzite and serpentine a clearly recognizable colour enhancement occurs. Therefore, it is recommendable to test on a sample piece or an inconspicuous area.
- On some natural stones like e.g. Nero Assoluto or Nero Impala the stone-imminent structures may be stronger intensified than the residual stone surface if treated with AKEMI® Natura Impregnator. This might be seen as staining, however, the colour intensification is not a product defect but is attributed to the characteristics of the stone.
- For proper waste disposal, the container must be completely emptied.

**Technical Data:**

Coverage:	up to 25 m <sup>2</sup> /liter, depending on the absorptivity of the stone
Colour:	milky white
Density:	approx. 1 g/cm <sup>3</sup>
pH value:	approx. 7

**Storage:** If stored in dry and cool condition (5-25°C/41-77°F) in its closed original container at least 24 months from production.

**Health & Safety:** Read Safety Data Sheet before handling or using this product.

**Important Notice:** The above information is based on the latest stage of development and application technology. Due to a multiplicity of different influencing factors, this information – as well as other oral or written technical advises – must be considered as non-binding hints. The user is obliged in each particular case to conduct performance tests, including but not limited to trails of the product, in an inconspicuous area or fabrication of a sample piece.

TDS 06.21